

207. Derbigum GC

CE	
0749	
Date and reference of data sheet	: 06/01/2009 Réf. 207
Product trade name	: DERBIGUM GC
Producer	: IMPERBEL SA – Perwez - Belgium
EC Certificate - year and number	: 07 BC2-310-0305-123-01
European standard reference	: EN 13707
Product description	: Plastomeric modified bitumen Reinforcements : Glassmat + Non-woven polyester Surfacing : upper side : fine mineral back side : talk Method of application : torched Roofing system : top layer single layer not for roof gardens

Packaging :				
Characteristics	Test method / Classification	Units	Expression of result	Values
Thickness	EN 1849-1	mm	MDV	4(± 0,2)
Length (1)	EN 1848-1	m	MLV	10
Width	EN 1848-1	m	MLV	1,10
Surface (1)	-	m ²	MLV	11
Mass per unit area	EN 1849-1	kg/m ²	MDV	4,300 (± 10%)
Roll weight (1)	-	kg	MDV	46(± 2)
Number of rolls per pallet (1)	-	-	-	20

(1) Values for standard products

207. Derbigum GC

Product performance :				
Characteristics	Test method / Classification	Units	Expression of result	Values or statement
Watertightness	EN 1928 / A	-	-	Pass
External fire performance	ENV 1187-1	-	Classification according to EN 13501-5	B _{ROOF} (t1)
Reaction to fire	ISO 11925-2	-	Classification according to EN 13501-1	E
Shear resistance of joint	EN 12317-1	N/50mm	MDV	800 (± 20%)
Maximum tensile force : - longitudinal direction - transverse direction	EN 12311-1	N/50mm	MDV	1200 (± 20%) 1200 (± 20%)
Tensile elongation : - longitudinal direction - transverse direction	EN 12311-1	%	MDV	50 (± 15) 50 (± 15)
Resistance to impact	EN 12691:2006 (Method B)	mm	MLV	2000
Resistance to static loading	EN 12730 (Method A)	kg	MLV	25
Dimensional stability	EN 1107-1	%	MLV	≤0.2
Flexibility at low temperature	EN 1109	°C	MLV	- 15
Flow resistance at elevated temperature	EN 1110	°C	MLV	140
Artificial ageing to elevated temperature : - Flow resistance at elevated temperature	EN 1296 EN 1110	°C	MDV	≥140
Artificial ageing to UV + elevated temperature + water : - Visible defects	EN 1297 EN 1850-1	-	-	No visible defects
MLV=Manufacturer's limiting value MDV=Manufacturer's declared value NPD=No Performance Determined				